

Flowable composite

Light-curing flow composite for direct restorations, relinings as well as for sealing fissures. For cavities according to Black's classes I, II, III, and V, which are placed in areas without masticatory load.

Eigenschaften	Vorteile
low viscosity	easy to apply
thixotrope behavior	high stability, no running or dripping
very good mechanical properties	long-lasting restorations
wide choice of shades	natural restoration
good radiopacity	x-ray check possible
medium filler particle	highly polishable



Shades: Vita-shades A1-A4, B2-B4 and C3
Packaging sizes: 1 g- and 2 g-syringe
Shelf-life: Max. 4 years
Storage: 10 -25°C

Technische Daten:

Vickers hardness >374 MPa
Flexural strength >134 MPa
E-Module >6998 MPa
Compressive strength >403 MPa

Version 10/2014